—SAATI

Fixer 6

Emulsion Hardener

Applications

Increases stencil water resistance for more impressions per screen.

Characteristics

- Works as a catalyst with triple-cure emulsions
- (Ceramic HT, Textil HT, Vitrum HT) or makes a permanent, solvent-resistant and waterproof stencil
- Works as an emulsion hardener with water-resistant emulsions such as Textil DW and Textil DT to make a more durable stencil

Directions For Use

Apply SAATI Fixer 6 thinly and evenly to both sides of the dry stencil with a sponge, brush or cloth. Remove Fixer 6 excess to avoid drips with vacuum or airjet. Allow Fixer 6 to penetrate emulsion. Then cure overnight at room temperature or for one or two hours at 50º to 60ºC.

Health And Safety

Before using, refer to appropriate Safety Data Sheets. Contact SAATI at info.IT@saati.com to request SDS.

Storage

When sealed in the original container and stored in cool conditions, SAATI products will maintain their original properties for one year from the date of production.

Packaging

Available in 1 and 10 kilogram containers.