

Coated Aramid Fabrics for Vehicle Armouring

SAATI Protection - Product Range

Phenolic Systems

Item	Weave	Resin content	Prepreg Weight	Curing Cycle		
		(%)	(g/m ²)	(°C)	(bar)	(min)
Style 258 PHLF - single side coated	Plain	12	455	165	30	★
Style 101 PHLF - single side coated	Plain	16	525	165	30	★
Style 258 PHLF - double side coated	Plain	25	535	165	30	★
Style 350 PHLF - single side coated	Basket 3/3	9	374	165	30	★

Rubberized Systems

Item	Weave	Resin content	Prepreg Weight	Curing Cycle		
		(%)	(g/m ²)	(°C)	(bar)	(min)
Style 101 GRCD PLUS - double side coated	Plain	18	580	175	10 - 50	★
Style 101 GHY - single side coated	Plain	15	515	185	10 - 50	★