

Finish SU1 A&B

Two Part Polyurethane Screen Sealer

Applications

Provides protective coating for frame adhesive and permanently replaces blockout tape.

Characteristics

- Red water-based two part polyurethane
- Easy to apply by scoop coater, brush or scraper
- Tack free immediately after drying
- One hour plus mixed pot life
- Gains 100% water, solvent and corrosive resistance after curing for 24 hours

Features/Benefits

- Low odor, non flammable and easy to mix & apply
- Water based formula – does not attack & weaken frame adhesive
- Can be applied onto freshly dry glue on stretching table – to accelerate full cure & bonding

Directions For Use

Mix Finish SU1 as follows:

Finish SU1 comp. a 1000 g

Finish SU1 comp. b 500 g

Thinner Finish SU1 500 g

until a good uniformity and acceptable viscosity is obtained.

Apply Finish SU1 A+B with a coating trough on both sides of the screen placed in a vertical position, then remove the lacquer from the open areas with a sucking unit.

The screen should be placed on its special stand to let the lacquer dry. A complete hardening of Finish SU1 a+b is obtained in approximately 24 hours at room temperature (20/25°C). If drying of Finish SU1 a+b delay due to low humidity conditions, we suggest to use our Activator Conc. in a ratio of 2–4% over Finish SU1 quantity.

Health & Safety

Before using, refer to appropriate Safety Data Sheets. Contact SAATI at info.IT@saati.com to request SDS.

Storage

When sealed in the original container and stored in cool conditions, SAATI products will maintain their original properties for one year from the date of production.

Packaging

FINISH SU1 comp. a 1 and 5 kg

FINISH SU1 comp. b 1 and 5 kg

Thinner Finish SU1 0.750, 5 and 20 kg

Activator Conc. 1 kg.