

Project: Location: To:



SAATI Via Milano 14 Appiano Gentile - Italia

None

Tel: 031933392 Fax: E-Mail: None

Energy values		EN410/EN673
Ug	Thermal Transmittance	1.0 W/m²K
g	Solar Factor	24%
αtot	Total Absorption	60%

Light Values

Τv	Light Transmission	33%
ρν	External Light Reflection	19%
ρν'	Internal Light Reflection	26%
Ra	General Color Rendering Index	96

Configuration (External -> Internal)



Technical Data

↔	Thickness	31.5 mm
	Weight	38.8 Kg/m²
1	Noise Reduction [Rw(C;Ctr)dB]	40(-2;-6)



The extensive version of this gA-Report, with more than 20 figures illustrated, may be analyzed through tablet or smartphone using this QR code, or through a desktop computer clicking on the link below.

https://app.glassadvisor.com/configurator/ad957f9f2bcff32fa8ea4023fc41



gA-Report

No.: gA-258512-2025 gA version: 1.0 Date: 07-05-2025 Username: Paolo

Glassadvisor GmbH Srl

Horazstraße 19, Via Orazio 19 39100 Bozen, Bolzano (BZ) Italia

info@glassadvisor.com www.glassadvisor.com P.I. 02903760219



The version 1.0 of glassAdvisor has been verified by Stazione Sperimentale del Vetro and is compliant to EN673, EN410 and its Annex B.

The manufacturers of materials used in the simulation and glassAdvisor Srl can not be held responsible for any differences between the data hereby presented and those observed in reality. The spectra of the simulated materials are subject to tolerances in accordance to the relevant product standards and are subject to change without previous notice. Accessing the soft-copy version of this report may cause a recalculation of the results according to updated algorithm and/or database, the values may differ from the hardcopy. The possibility to simulate this product configuration does not guarantee the availability of the same in the market. The values are referred to the center of the glass, do not consider the effects of the edge and are executed according to one or more of the following norms and attachments: EN ISO relevant 52022-3, EN673, EN410, DT210, EN16612, EN13363-2 and ISO15099. The noise reduction values have a tolerance of +-2dB and are obtained from a valabase of measurements producers certification supplied by producers, users or available in the market. The noise reduction estimation is obtained from a certified value, through average or interpolation of two or more values, do not refer to specific commercial products, and may not be used as an official certificate from a third party laboratory. Occasionally and without prior notice, glassAdvisor GmbH reserves the right to remove or update such values thus obsoleting any previous data. Copyright © - 2024 - All rights reserved - Glassadvisor GmbH