

Aramid Fabrics

SAATI Protection - Product Range

Item	Weave	Threads x cm		Title Count		Thickness	Weight	Warp	Weft
		Warp (n°/cm)	Weft (n°/cm)	Warp (dtex)	Weft (dtex)	(mm)	(g/m²)	(DaN/cm)	
270	plain	27,5	27,5	Kevlar 159 220	Kevlar 159 220	0,20	125	80	100
372	plain	23,2	23,2	Kevlar 159 330	Kevlar 159 330	0,22	158	100	100
310	plain	14,0	14,0	Kevlar KM2+440	Kevlar KM2+ 440	0,17	125	100	100
431	plain	12,2	12,2	Kevlar KM2+440	Kevlar KM2+ 440	0,13	110	90	90
6402	plain	10,7	10,7	Kevlar KM2+670	Kevlar KM2+ 670	0,20	145	130	130
6602	plain	12,2	12,2	Kevlar KM2+670	Kevlar KM2+670	0,25	165	135	135
3631	plain	10,7	10,7	Kevlar KM2+940	Kevlar KM2+940	0,31	200	140	140
3651	plain	11,7	11,7	Kevlar KM2+940	Kevlar KM2+ 940	0,32	220	150	150
802	plain	8,5	8,5	Kevlar KM2+1100	Kevlar KM2+ 1100	0,26	190	150	150
812	plain	12,2	12,2	Kevlar KM2+1100	Kevlar KM2+ 1100	0,38	280	220	220
863	plain	9,3	9,3	Kevlar KM2+1100	Kevlar KM2+ 1100	0,33	205	140	140
865	plain	10,0	10,0	Kevlar KM2+1100	Kevlar KM2+1100	0,27	220	170	170
258	plain	6,4	6,4	Kevlar 129 3140	Kevlar 129 3140	0,62	410	320	350
300	plain	4,5	4,5	Kevlar 29 3300	Kevlar 29 3300	0,40	300	190	190
101	plain	6,7	6,7	Kevlar 29 3300	Kevlar 29 3300	0,63	460	280	280
103	twill 4/4	9,3	9,3	Kevlar 29 3300	Kevlar 29 3300	0,91	635	320	320

● for spike protection

All items can be provided with water repellency, scoured or heatset treatment.