

Technical Data Sheet

Traditional Woven Fabrics

Item	Weave	Threads x cm		Title Count		Thickness (mm)	Weight (g/m ²)	Warp (DaN/cm)	Weft (DaN/cm)
		Warp (n°/cm)	Weft (n°/cm)	Warp (dtex)	Weft (dtex)				
310	plain	14,0	14,0	Kevlar KM2+440	Kevlar KM2+440	0,17	125	100	100
431	plain	12,2	12,2	Kevlar KM2+440	Kevlar KM2+ 440	0,13	110	90	90
6402	plain	10,7	10,7	Kevlar KM2+670	Kevlar KM2+670	0,20	145	130	130
6602	plain	12,2	12,2	Kevlar KM2+670	Kevlar KM2+670	0,25	165	135	135
3631	plain	10,7	10,7	Kevlar KM2+940	Kevlar KM2+940	0,31	200	140	140
3651	plain	11,7	11,7	Kevlar KM2+940	Kevlar KM2+940	0,32	220	150	150
802	plain	8,5	8,5	Kevlar KM2+1100	Kevlar KM2+1100	0,26	190	150	150
812	plain	12,2	12,2	Kevlar KM2+1100	Kevlar KM2+1100	0,38	280	220	220
863	plain	9,3	9,3	Kevlar KM2+1100	Kevlar KM2+1100	0,33	205	140	140
865	plain	10,0	10,0	Kevlar KM2+1100	Kevlar KM2+1100	0,27	220	170	170
258	plain	6,4	6,4	Kevlar 129 3140	Kevlar 129 3140	0,62	410	320	350
300	plain	4,5	4,5	Kevlar 29 3300	Kevlar 29 3300	0,40	300	190	190
101	plain	6,7	6,7	Kevlar 29 3300	Kevlar 29 3300	0,63	460	280	280
103	twill 4/4	9,3	9,3	Kevlar 29 3300	Kevlar 29 3300	0,91	635	320	320