

# Saatifil® Polypropylene

Product No.	Mesh Opening	Open Area	Mesh Count		Thread Diameter	Weight		Thickness	Permeabilità all'aria 20 mm CA	Availability
Articolo	Apertura Maglie	Superficie libera	Numero Fili		Diametro Filo	Peso		Spessore	Air Permeability 20 mm WG	Disponibilità
Gewebe Nr.	Maschenweite	Offene Siebfläche	Fadenzahl		Drahtdurchmesser	Gewicht		Dicke	Luftdurchlässigkeit 20 mm WS	Verfügbarkeit
	µm	%	n/cm	n/inch	µm	g/m <sup>2</sup>	oz/sq.yd	µm	l/ m <sup>2</sup> s	
PP 106/26	106	26	47	119	100	70	2,1	195	5000	•••
PP 200/44	200	44	32	81	100	46	1,36	170	7550	•••
PP 210/32	210	32	27,5	70	150	98	2,9	315	n.a.	•
PP 230/27	230	27	22	56	200	133	3,9	340	n.a.	•••
PP 297/35	297	35	20	51	200	125	3,7	420	n.a.	••
PP 350/32	350	32	16,7	42	250	172	5,1	525	n.a.	••
PP 460/47	460	47	15	38	200	92	2,7	390	n.a.	•
PP 500/36	500	36	12	30	320	180	5,3	690	7500	•••
PP 980/47	980	47	7	18	490	250	7,4	1250	7900	•••

PP = polypropylene / polipropilene / polypropylen

••• item routinely produced | •• standard item | • item produced on demand

I dati tecnici sopra indicati, escluso il diametro filo per il quale è espresso un valore nominale, si riferiscono ai valori medi riscontrati su campioni della produzione e sono soggetti a possibili modifiche, in conformità alla nostra politica di continuo miglioramento del prodotto.

The listed technical specifications, exception made for the thread diameter indicated with its nominal value, are referred to the arithmetic mean value of production samples and are subject to change, in accordance with our policy of continuously improving our products.

O.G. technische Daten beziehen sich auf durchschnittlichen Werte, die bei Produktionsmustern festgestellt wurden, mit Ausnahme von Fadendurchmesser, wofür der Nominalwert ausgedrückt wird. Im Einklang unserer Geschäftspolitik, die die dauernde Kontrolle und Verbesserung unserer Produkten definiert, behalten wir uns die Änderung der technischen Daten jederzeit vor.

## World Headquarters

SAATI S.p.A  
Via Milano 14  
22070 Appiano Gentile (CO)  
Italy  
T. +39 031 9711  
F. +39 031 933392  
info.IT@saati.com  
Web site: www.saati.com

## Branches:

**SAATI Americas Corp.**  
201 Fairview Street Extension  
Fountain Inn, SC USA 29644  
T: +1 (864) 601-8300  
info.US@saati.com

**SAATI Deutschland GmbH**  
Ostring 22, 46348 Raesfeld  
Germany  
T: +49 2865 95800  
info.DE@saati.com

**SAATI France**  
74 Route de Bapaume 80360  
Sailly Saillisel, France  
T: +33 3 22 857700  
saatifrance@saati.com

**SAATI Technical Fabric (Tianjin) CO., LTD.**  
Cross of Saida 2nd Branch Road and  
Saida Century Avenue,  
Xiqing Economic Development Area,  
Tianjin, China, 300385  
T: +86 22 23960843  
info.CN@saati.cn

**SAATI Serigrafia Iberica, S.A.**  
P.I. Mijares - C/ Industria, 13  
12550 Almazora- Castellon,  
Spain  
T: +34 96.45.50.688  
info.ES@saati.com

**SAATI Korea LTD.**  
SK Ventium 101-601  
166, Gosan-ro, Gunpo-si,  
Gyeonggi-do, Republic of Korea  
T: +82 31 429 9337  
info.KR@saati.com