

SAATILene Hi-Dro

Article	Mesh Count		Nominal Thread Diameter	Mesh Opening	Open Area	Fabric Thickness	Theoretical ink Volume	Specif Cross-Section	maximum recommended tension from-to
	n°/cm	n°/inch	µm	µm	%	µm	cm ³ /m ²	mm ² /cm	N/cm
PE AM 32.70 PW	32	81	70	245	61	110	67	0,123	30-35
PE AM 43.64 PW	43	110	64	170	53	100	53	0,138	28-32
PE AM 48.55 PW	48	112	55	153	55	90	50	0,185	24-26
PE AM 55.48 PW	55	140	48	125	50	78	39	0,099	28-30
PE AM 62.48 PW	62	157	48	109	46	77	35	0,112	28-30
PE AM 78.40 PW	78	198	40	85	44	65	29	0,098	24-28
PE AM 90.40 PW	90	229	40	68	38	62	24	0,113	20-24
PE AM 120.31 PW	120	305	31	53	40	48	19	0,091	21-24

The above data are average values measured on piece-good in relaxed state, manufactured with yarns of a perfect nominal diameter (cfr. international standards), under normal hygrometric conditions (20°C=68°F, 65% relative humidity). They are subject to normal variations up to 7% if conditions vary from those stated above. The listed technical specifications, exception made for the thread diameter indicated with its nominal value, are referred to the arithmetic mean value of production samples and are subject to change, in accordance with our policy of continuously improving our products.

The tension tests are realised with TOP 12 series clamp system and appropriate frames at our laboratories.

PW: plain weave (1:1)