


Technical data sheet

## SAATILENE HI-TEX

Saatilene Hitex is a high modulus, low elongation monofilament polyester screen printing fabric designed as the entry level fabric for the traditional and particularly competitive screen printing applications, like t-shirt printing, textiles and ceramic.

The product is available in the range from 0 to 120 mesh count per cm, in standard production width and only in white and yellow color. The product has also no surface treatment, thus it requires proper degreasing and mesh preparation.



### PRODUCT CHARACTERISTICS:

- Competitive price
- Consistent Saati quality
- Focused specification range
- No surface treatment

### YOUR BENEFITS:

- Excellent price/performance ratio.

Article	Mesh count		Nominal thread diameter	Mesh opening	Open Area	Fabric thickness	Theoretical ink volume	Specific cross-section	Maximum recommended tension from-to
	n°/cm	n°/inch	µm	µm	%	µm	cm <sup>3</sup> /m <sup>2</sup>	mm <sup>2</sup> /cm	N/cm
PE AM 6,5.385 PW	6,5	17,0	385	1180	58	700	406	0,756	35-60
PE AM 9,5.280 PW	9,5	24	280	810	55	533	293	0,585	35-60
PE AM 10,5.260 PW	10,5	27	260	700	52	478	249	0,557	35-60
PE AM 12.145 PW	12	30	145	700	68	270	184	0,198	35-60
PE AM 12.260 PW	12	30	260	580	47	485	228	0,637	35-60
PE AM 15.200 PW	15	38	200	475	50	365	183	0,471	35-60
PE AM 15.260 PW	15	38	260	400	35	460	161	0,796	35-60
PE AM 18.160 PW	18	46	160	400	52	285	148	0,362	35-60
PE AM 21.160 PW	21	53	160	330	46	285	131	0,422	35-60
PE AM 24.120 PW	24	61	120	290	50	216	108	0,271	35-60
PE AM 24.145 PW	24	61	145	275	43	265	114	0,396	35-60
PE AM 27.120 PW	27	69	120	250	44	222	98	0,305	35-60
PE AM 27.145 PW	27	69	145	220	35	255	89	0,446	35-60
PE AM 29.120 PW	29	74	120	220	41	218	89	0,328	35-60
PE AM 29.145 PW	29	74	145	190	32	258	83	0,479	35-60
PE AM 32.70 PW	32	81	70	245	61	110	67	0,123	24-26
PE AM 32.100 PW	32	81	100	200	43	160	69	0,251	35-40
PE AM 32.120 PW	32	81	120	190	38	205	78	0,362	35-60
PE AM 34.100 PW	34	86	100	185	41	173	71	0,267	35-40
PE AM 36.90 PW	36	91	90	190	45	145	65	0,229	35-40
PE AM 36.100 PW	36	91	100	175	38	170	65	0,283	35-40
PE AM 38.90 PW	38	97	90	170	42	161	68	0,242	35-40
PE AM 40.80 PW	40	102	80	170	44	135	59	0,201	35-40
PE AM 40.90 PW	40	102	90	160	40	148	59	0,254	35-40
PE AM 43.80 PW	43	110	80	150	43	138	59	0,216	35-37
PE AM 45.70 PW	45	114	70	148	47	115	54	0,173	30-34
PE AM 49.70 PW	49	125	70	130	40	116	46	0,188	30-34
PE AM 49.80 PW	49	125	80	120	35	138	48	0,246	34-50
PE AM 51.70 PW	51	130	70	120	38	118	45	0,196	30-35
PE AM 55.64 PW	55	140	64	120	41	105	43	0,177	23-31
PE AM 55.70 PW	55	140	70	105	33	114	38	0,212	30-34
PE AM 62.64 PW	62	158	64	90	32	106	34	0,199	30-34
PE AM 68.55 PW	68	173	55	89	36	89	32	0,161	25-30
PE AM 71.55 PW	71	180	55	80	33	93	31	0,169	25-30
PE AM 77.48 PW	77	196	48	78	36	78	28	0,139	24-26
PE AM 77.55 PW	77	196	55	70	28	90	25	0,183	27-32
PE AM 90.40 PW	90	230	40	68	38	62	24	0,113	20-24
PE AM 90.48 PW	90	230	48	55	27	81	22	0,163	27-29
PE AM 100.40 PW	100	255	40	55	31	63	20	0,126	26-28
PE AM 100.48 PW	100	255	48	40	16	81	13	0,181	30-34
PE AM 110.34 PW	110	280	34	53	35	56	20	0,100	22-24
PE AM 110.40 PW	110	280	40	47	26	64	17	0,138	25-30
PE AM 120.31 PW	120	305	31	53	40	48	19	0,091	21-24
PE AM 120.34 PW	120	305	34	45	29	54	16	0,109	24-26
PE AM 120.40 PW	120	305	40	38	20	67	13	0,151	27-32

The above data are average values measured on piece-good in relaxed state, manufactured with yarns of a perfect nominal diameter (cfr. international standards), under normal hygrometric conditions (20°C=68°F, 65% relative humidity). They are subject to normal variations up to 7% if conditions vary from those stated above.

The listed technical specifications, exception made for the thread diameter indicated with its nominal value, are referred to the arithmetic mean value of production samples and are subject to change, in accordance with our policy of continuously improving our products.

The tension tests are realised with TOP12 series clamp system and appropriate frames at our laboratories.

PW: Plain Weave (1:1).