

ULTRAFIX SB9 plus

APPLICATIONS

Frame adhesives.

GENERAL CHARACTERISTICS

- Two-components polyurethane adhesive
- Low percentage of acetone
- Red color ,medium viscosity, for coarse and medium mesh counts
- Very good initial adhesion allows to glue screen mesh on aluminum pre-treated surface ,iron, steel ,plastic coated and wood frames
- Drying time, between approx15-30 minutes ,depend on mesh count end environmental local temperature condition
- Ultrafix SB9 Plus is low viscosity adhesive for medium to fine mesh-count fabrics.

DIRECTIONS FOR USE

Mix 100 parts of Ultrafix SB9 Plus with 20 part of Catalyst by weight. The mixture prepared is ready to use and suitable to paste fabrics from 32 threads /cm without addition thinner. Use within 60 to 90 minutes.

To obtain optimal adhesion, degrease the frame. Stretch the fabric over the frame providing good contact between the two. Apply the prepared mixture with a brush. After the adhesive has dried and cured (drying time depend of mesh count fabrics and environmental local temperature condition)release tension and remove the screen from the stretching system.

HEALTH AND SAFETY

Before using, refer to appropriate material safety data sheets.

STORAGE

When sealed in the original container and stored in cool conditions, ULTRAFIX SB9 Plus will maintain original properties for 24 months from the date of production.

WARNING :

In winter time packages of adhesive exposed to low temperatures (close to 0°C) could increase quite a lot adhesive viscosity.

In case, keep containers in a warm place or, to short the process, place them in a hot air oven (40-45°C) for several hours. Operating in this way is possible to recover original conditions of the adhesive without deteriorations.

PACKAGING

ULTRAFIX SB9 Plus is available in 0,75, 4,5 kilogram containers.

CATALYST ULTRAFIX SB9 Plus is available in 0,15 and 0,9 kilogram containers.

WARRANTY AND LIMITED REMEDY

The directions, recommendations and specifications contained in this Technical Data Sheet are meant as a guide to the use of the product and shall not bind the company. Product specifications are subject to change without notice.

The following is made in lieu of all other expressed or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose: all Saatichem manufactured liquid products are warranted to be free of defects in materials and manufacture and to meet the specifications stated in Saatichem applicable Product Bulletin. Saatichem will replace or refund the price of any Saatichem manufactured liquid product that does not meet this warranty within the applicable warranty period.

The remedies are exclusive. In no case shall Saatichem be liable for any other direct or indirect damage or loss, including without limitation any incidental, special or consequential damages, or any material costs or labor charges incident to the removal or replacement of any mesh, screen, ink, substrate, finished graphic or any other item.